



US 20060062824A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2006/0062824 A1**
Pacetti et al. (43) **Pub. Date: Mar. 23, 2006**

(54) **MEDICATED COATINGS FOR
IMPLANTABLE MEDICAL DEVICES
INCLUDING POLYACRYLATES**

(21) Appl. No.: **10/948,036**

(22) Filed: **Sep. 22, 2004**

(75) Inventors: **Stephen Dirk Pacetti**, San Jose, CA
(US); **Thierry Glauser**, Redwood City,
CA (US)

Publication Classification

(51) **Int. Cl.**
A61F 2/00 (2006.01)

(52) **U.S. Cl.** **424/423**

Correspondence Address:
SQUIRE, SANDERS & DEMPSEY LLP
1 MARITIME PLAZA
SUITE 300
SAN FRANCISCO, CA 94111 (US)

(57) **ABSTRACT**

(73) Assignee: **Advanced Cardiovascular Systems,
Inc.**

A polymer for a medical device, particularly for a drug eluting stent, is described. The polymer can be derived from n-butyl methacrylate and can have a degree of an elongation at failure from about 20% to about 500%

**MEDICATED COATINGS FOR IMPLANTABLE
MEDICAL DEVICES INCLUDING
POLYACRYLATES**

BACKGROUND

[0001] 1. Field of the Invention

[0002] This invention is directed to coatings for implantable medical devices, such as drug eluting vascular stents.

[0003] 2. Description of the State of the Art

[0004] Percutaneous transluminal coronary angioplasty (PTCA) is a procedure for treating heart disease. A catheter assembly having a balloon portion is introduced percutaneously into the cardiovascular system of a patient via the brachial or femoral artery. The catheter assembly is advanced through the coronary vasculature until the balloon portion is positioned across the occlusive lesion. Once in position across the lesion, the balloon is inflated to a predetermined size to radially compress the atherosclerotic plaque of the lesion to remodel the lumen wall. The balloon is then deflated to a smaller profile to allow the catheter to be withdrawn from the patient's vasculature.

[0005] A problem associated with the above procedure includes formation of intimal flaps or torn arterial linings, which can collapse and occlude the conduit after the balloon is deflated. Moreover, thrombosis and restenosis of the artery may develop over several months after the procedure, which may require another angioplasty procedure or a surgical by-pass operation. To reduce the partial or total occlusion of the artery by the collapse of arterial lining, and to reduce the chance of the development of thrombosis and restenosis, a stent is implanted in the lumen to maintain vascular patency.

[0006] Stents are used not only as a mechanical intervention but also as a vehicle for providing biological therapy. As a mechanical intervention, stents act as scaffoldings, functioning to physically hold open and, if desired, to expand the passageway. Typically, stents are capable of being compressed, so that they can be inserted through small vessels using catheters, and then expanded to a larger diameter once they are at the desired location. Examples in the patent literature disclosing stents that have been applied in PTCA procedures include stents illustrated in U.S. Pat. No. 4,733,665 issued to Palmaz, U.S. Pat. No. 4,800,882 issued to Gianturco, and U.S. Pat. No. 4,886,062 issued to Wiktor.

[0007] Pharmacological therapy can be achieved by medicating the stents. Medicated stents provide for the local administration of a therapeutic substance at the diseased site. In order to provide an effective concentration at the treated site, systemic administration of such medication often produces adverse or toxic side effects for the patient. Local delivery is a preferred treatment method in that smaller total medication levels are administered compared to systemic dosages, but are concentrated at a specific site. Local delivery thus produces fewer side effects and achieves better results. One proposed method for medicating stents involves using a polymeric carrier coated onto the stent's surface. A solution, which includes a solvent, a polymer dissolved in the solvent, and a therapeutic substance dispersed in the blend is applied to the stent. The solvent is allowed to evaporate, leaving a coating of the polymer and the therapeutic substance impregnated in the polymer on the stent surface.

[0008] One polymer that can be used for making stent coatings is poly(n-butyl methacrylate) (PBMA). This polymer is durable, and biologically compatible, and can be used either as a polymeric matrix carrying the drug, or as a topcoat membrane regulating the release rate of the drug. However, PBMA has properties that can be improved. In particular, the release rate of some hydrophobic, medium-molecular-weight drugs, such as EVEROLIMUS, from the PBMA-based stent coatings can be too low. As a result, a higher drug-to-polymer ratio may be required, which is undesirable. At high drug-to-polymer ratios, some of the PBMA-based drug and polymer compositions can have insufficient elongation at high strains that expansion of the stent creates in the coating.

[0009] The embodiments of the invention provide stent coatings that are free of the above-described deficiencies and possess other beneficial properties.


SUMMARY

[0010] Various embodiments encompass medical articles comprising a polymer derived from a base polymer comprising residues of a base monomer (which when polymerized yields the base polymer), wherein the base polymer has a degree of elongation at failure of from 20-500%. In some of these embodiments, the polymer comprises a base polymer with a weight-average molecular weight of about 200 k-1000 k Daltons. In these or other embodiments, the base polymer has a polydispersity index of about 3 to about 6. In these or other embodiments, the polymer has a glass transition temperature of below about 20° C.; alternatively from -30 to 20° C.



[0011] In these or other embodiments, the polymer includes at least a first acrylic monomer. Some embodiments select the polymer to be a mixture of at least a first acrylic monomer and the base polymer; some select the polymer to be a copolymer of base monomers and first acrylic monomers.

[0012] In these or other embodiments, the first acrylic monomer is at least one of n-hexyl methacrylate, 2-ethylhexyl methacrylate, lauryl methacrylate (dodecyl methacrylate), n-octyl methacrylate, n-heptyl methacrylate, n-nonyl methacrylate, 2-ethoxyethyl methacrylate, 2-methoxyethyl methacrylate, pentyl methacrylate, iso-decyl methacrylate, n-decyl methacrylate, n-dodecyl methacrylate), 1-hexadecyl methacrylate, undecyl methacrylate, 3,5,5-trimethylhexyl methacrylate or an combination of these monomers. In some embodiments, the first acrylic monomer is chosen from a group that specifically excludes any one or any combination of these monomers.

[0013] In some embodiments, the polymer has one of the following formulas:



-continued



[0014] wherein X and X₁ are each, independently, a hydrogen atom or an alkyl group, R and R₁ are each, independently, a C₁-to-C₁₋₂ straight-chained or branched aliphatic radical, and m, n, and p are each integers in which m > 0, n > 0, and p ≥ 0.

[0015] In these or other embodiments, the base polymer comprises at least one of or any combination of poly(n-butyl methacrylate), poly(ethyl methacrylate), poly(isopropyl methacrylate), or poly(n-propyl methacrylate). In some embodiments, the base polymer is chosen from a group that specifically excludes any one or any combination of these.

[0016] In these or other embodiments, the polymer comprises poly(n-butyl methacrylate) and a second polymeric material wherein the polymer has a substantially single, glass transition temperature. In some of these embodiments, that substantially single, glass transition temperature is below about 20° C.; alternatively from -30° C. to about 20° C.

[0017] In these or other embodiments, the second polymeric material is at least one of poly(n-hexyl methacrylate), poly(n-heptyl methacrylate), poly(2-ethylhexyl methacrylate), poly(n-octyl methacrylate), poly(n-nonyl methacrylate), poly(2-ethoxyethyl methacrylate), poly(2-methoxyethyl methacrylate), poly(pentyl methacrylate), poly(isodecyl methacrylate), poly(n-decyl methacrylate), poly(1-hexadecyl methacrylate), poly(undecyl methacrylate), poly(3,5,5-trimethylhexyl methacrylate), poly(lauryl methacrylate), or an combination of these. In some embodiments, the second acrylic monomer is chosen from a group that specifically excludes any one or any combination of these monomers.

[0018] In these or other embodiments, the second polymeric material comprises a non-acrylic polymer with a T_g below that of the base polymer.

[0019] In these or other embodiments, the medical device additionally comprises one or any combination of these agents: vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, anti-thrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these. In some embodiments, the agents are chosen from a group that specifically excludes any one or any combination of these categories.

[0020] Methods of making the embodiments discussed above are also within the scope of this invention.

[0021] In some invention embodiments, the implantable medical device is a stent.

DETAILED DESCRIPTION

Terms and Definitions.

[0022] The following terminologies and definitions apply:

[0023] The term “polymer” is defined to be inclusive of homopolymers, copolymers, and terpolymers. The term “polymer” is further defined as a synonym of the term “polymeric compound”. The term “copolymer” is defined as a polymer derived from more than one species of monomer, including copolymers that are obtained by copolymerization of two monomer species and those obtained from three monomers species (“terpolymers”). The term “random copolymer” is defined as a copolymer consisting of macromolecules in which the probability of finding a given monomeric unit at any given site in the chain is independent of the nature of the adjacent units. The term “alternating copolymer” is defined as a copolymer consisting of macromolecules comprising two species of monomeric units in alternating sequence.

[0024] The term “polydispersity”, expressed as the polydispersity index (PI), refers to the molecular weight distribution of a polymer, since every polymer comprises molecules having a variety of chain lengths and thus a variety of molecular weights. The term “polydispersity index” is defined as the ratio M_w/M_n of the weight-average molecular weight of a polymer (M_w) to the number-average molecular weight of the same polymer (M_n).

[0025] The term “weight-average molecular weight” (M_w) is defined as the molecular weight of a polydisperse polymer sample, averaged to give higher statistical weight to larger molecules; calculated as

$$M_w = \frac{\sum(M_i^2 N_i)}{\sum(M_i N_i)},$$

where M_i is a molecular weight of a macromolecule of a fraction “i”, and N_i is a number of macromolecules in the “i” fraction.

[0026] The term “number-average molecular weight” (M_n) is defined as the molecular weight of a polydisperse polymer sample, averaged to give equal statistical weight to each molecule, calculated as


$$M_n = \frac{\sum(M_i N_i)}{\sum(N_i)},$$

where M_i and N_i are as defined above.

[0027] For most polymers, it is a frequent phenomenon that $M_w > M_n$, and consequently $PI > 1.0$. As the polymer's molecular weight distribution becomes narrower, the PI value approaches 1.0, and vice versa. For a theoretically monodisperse polymer, $M_w = M_n$; and for such polymer $PI = 1.0$.

[0028] The term "glass transition temperature" or T_g is defined as a temperature approximately in the middle of the temperature region where, as a result of exposure of an amorphous or semi-crystalline polymer to an increasing temperature, the onset of segmental molecular motion in the chains of the polymer occurs, leading to the eventual transition of the polymer from a glassy solid to an amorphous solid at atmospheric pressure. In other words, the T_g is defined as an average temperature in the temperature region at which an amorphous polymer (or the amorphous regions in a partially crystalline polymer) changes from a hard and relatively brittle nature to a viscoelastic (rubbery) nature. For the purposes of the present invention, the T_g for all polymers discussed below has been determined using differential scanning calorimetry (DSC) when the polymer is in a dry state. DSC measures the change in heat capacity of a polymer as a function of temperature. The "dry state" means that a polymer contains less than about 1% of water (as a percentage of the polymer's weight).

[0029] The term "acrylic polymers" or "acrylates" refers to polymers (inclusive of homopolymers, copolymers, terpolymers, oligomers, and prepolymers) derived from monomers having an acrylic group (I) or methacrylic group (II)



[0030] The term "maximum elongation" or "elongation at failure" is defined as the fractional increase in length of a free film of a polymer at the film rupture point, when the sample is stretched at a constant rate in a unidirectional, linear fashion.

EMBODIMENTS OF THE INVENTION

[0031] The stent coating can be a multi-layer structure that can include any one or any combination of the following layers:

[0032] (a) a primer layer;

[0033] (b) a drug-polymer layer (also referred to as "reservoir" or "reservoir layer") or alternatively a polymer-free drug layer;

[0034] (c) a topcoat layer; or

[0035] (d) a finishing topcoat.

[0036] In some embodiments, the multilayer structure may specifically exclude any one or any combination of the layers listed above.

[0037] Each layer of the stent coating can be formed on the stent by dissolving a polymer or a blend of polymers in a solvent or a solvent mixture, and applying the resulting solution to the stent by spraying or immersing it in the solution. After application the solvent evaporates leaving a dry coating. Drying can be accelerated by conducting it at an elevated temperature.

[0038] To incorporate a drug into the reservoir layer, the drug can be combined with the polymer solution described above. Alternatively, a polymer-free reservoir can be made. To fabricate a polymer free reservoir, the drug can be dissolved in a suitable solvent or solvent mixture, followed by applying the solution by spraying or immersing the stent in the drug solution.

[0039] Instead of introducing the drug as a solution, it can be introduced as a colloidal system, such as a suspension in an appropriate solvent. To make the suspension, the drug can be dispersed in the solvent using conventional colloid chemistry techniques. Depending on a variety of factors, e.g., the nature of the drug, those having ordinary skill in the art can select the solvent for the suspension, as well as the quantity of drug dispersed in the solvent. The suspension can be mixed with a polymer solution, and the mixture can be applied to the stent as described above. Alternatively, the drug suspension can be applied to the stent without being mixed with the polymer solution.

[0040] The drug-polymer layer can be applied directly to at least part of the stent surface to serve as a reservoir for at least one active agent or drug, which is incorporated into the reservoir layer. The optional primer layer can be applied between the stent and the reservoir to improve drug-polymer adhesion to the stent. The topcoat layer, if used, can be applied over at least a portion of the reservoir, and can serve as a rate limiting membrane, which helps to control drug release rate. In some embodiments, the topcoat layer can be essentially free of any active agents or drugs; nevertheless, during topcoat formation, a quantity of drug, however small, can migrate into the topcoat from the drug-polymer layer. The optional finishing layer can be applied to all or a part of the stent surface to enhance stent biocompatibility.

[0041] According to an embodiment of the present invention, any or all layer(s) of the stent coating can be a polymer derived from poly(n-butyl methacrylate) (PBMA), poly(ethyl methacrylate) (PEMA), poly(isopropyl methacrylate) (PIPMA), poly(n-propyl methacrylate) (PPMA) or copolymers including units derived from PBMA, PEMA, PIPMA, or PPMA having a high degree of an elongation at failure, such as from about 20% to about 500%, more narrowly, from about 30% to about 300%, for example, from about 40% to about 200%. For purposes of this disclosure, all of these polymers are referred to collectively as base polymers. Additionally, base-polymer unit means any monomeric unit from which a base polymer can be derived. Some invention embodiments specifically exclude any one or any combination of the polymers or base-polymer units listed above from inclusion as base polymers or base-polymer units.

[0042] According to embodiments of the present invention, various methods can be used to fabricate stent coatings that include base polymer or a base-polymer-unit-derived polymer with a high degree of elongation at failure. The following discussion describes these methods, which include:

[0043] using a base polymer having high weight-averaged molecular weight (M_w):

[0044] using a base polymer having a broad polydispersity index (PI); and

[0045] using a base-polymer-unit-derived polymeric compositions having lower T_g than that of base polymer.

[0046] Using a High- M_w Base Polymer

[0047] According to an embodiment of the present invention, base polymers having high M_w can be used. For example, useful base polymer M_w can be about 100,000 Daltons to about 1,000,000 Daltons. Viscosity may be an issue at 1,000,000 MW, but adjusting the application of a viscous solution or adjusting the viscosity of a solution is within the skill level of ordinarily skilled artisans.

[0048] In some embodiments, base polymers can have M_w from about 200,000 Daltons to about 600,000 Daltons, for example, from about 250,000 Daltons to about 500,000 Daltons.

[0049] Besides achieving higher degree of elongation at failure, using high molecular weight base polymers to make stent coatings is expected to improve many physical and mechanical properties of the coating. For example, tensile strength, yield strength, crack resistance, and abrasion resistance are all expected to improve.

[0050] Using Broad-PI Base Polymers

[0051] In some embodiments, in order to have base polymer with a high degree of elongation at failure, base polymer with a broad molecular weight distribution are used. For example, base polymer having a PI from about 3 to about 6 can be used. In other embodiments, M_w can range from about 300,000 Daltons to about 1,000,000 Daltons, as described above, and PI can range from about 3 to about 6.

[0052] Using Base-Polymer-Unit-Derived Polymeric Compositions with Reduced T_g





[0053] While typically it is beneficial to decrease the drug release rate, sometimes the drug release rate is too low. At those times, it is desirable to increase drug release rate. The drug release rate is related to the polymer's drug permeability. Permeability is the product of the drug solubility and drug diffusivity in the polymer. Solubility is a thermodynamic property of the drug in the polymer. In turn, drug diffusivity is related to polymer structure. Typically, the polymer has a higher ultimate elongation when it has a lower T_g and lower degree of crystallinity, if crystallinity is present. These same properties also lead to a higher drug diffusion rate through the polymer. Accordingly, in some invention embodiments, any or all layer(s) of the stent coating can be made of polymer compositions having reduced T_g . These compositions include a component derived from n-butyl methacrylate and a component derived from another acrylic compound. Such compositions can be of two types: first, the compositions comprising polymers that include units derived from a base-polymer-unit, and second, compositions that are physical blends of base polymer with at least one other acrylic polymer. Additionally, in some embodiments, any or all layer(s) of the stent coating can be made of polymer compositions having reduced T_g ,

the compositions including a component derived from base-polymer unit and a component derived from a non-acrylic compound.

Copolymers Including Units Derived From a Base-Polymer Unit

[0054] In some embodiments, the polymer composition can include a copolymer of a base-polymer unit with another acrylic monomer (base-polymer-unit copolymer (bpu copolymer)), where the T_g of the bpu copolymer is lower than that of the T_g of pure base polymer, which depends on molecular weight. The bpu copolymers can be of any kind, e.g., random, alternating, or block-copolymers. The T_g of a bpu copolymer can be below about 20° C., for example, between about -30° C. to about 20° C., alternatively, from about 0° C. to about 20° C., for example, about 15° C.

[0055] Base-polymer-unit copolymers having reduced T_g suitable for stent coatings can have an exemplary general formula (III-A), formula (III-B), formula (III-C), or formula (III-D):



wherein:




[0056] X and X_1 is each, independently, a hydrogen atom or an alkyl group, such as methyl or ethyl group;

[0057] R and R_1 is each, independently, a C_1 to C_{12} straight-chained or branched aliphatic radical; and

[0058] m, n, and p are each integers, where $m > 0$, $n > 0$, and $p \geq 0$.

[0059] The total molecular weight (M_w) of a polymer according to formulas (III-A to III-D) can be from about 50,000 Daltons to about 500,000 Daltons, alternatively, from about 100,000 Daltons to about 400,000 Daltons, such as about 250,000 Daltons.

[0060] Examples of base-polymer-unit copolymers described by formulas (III-A to III-D) include poly(n-butyl methacrylate-co-n-hexyl methacrylate), poly(n-butyl methacrylate-co-2-ethylhexyl methacrylate), poly(n-butyl methacrylate-co-n-octyl methacrylate), poly(n-butyl methacrylate-co-2-ethoxyethyl methacrylate), poly(n-butyl methacrylate-co-2-methoxyethyl methacrylate), poly(n-butyl methacrylate-co-pentyl methacrylate), poly(n-butyl methacrylate-co-iso-decyl methacrylate), poly(n-butyl methacrylate-co-n-decyl methacrylate), poly(n-butyl methacrylate-co-n-dodecyl methacrylate), poly(n-butyl methacrylate-co-1-hexadecyl methacrylate), poly(n-butyl methacrylate-co-undecyl methacrylate) poly(n-butyl methacrylate-co-3,5,5-trimethylhexyl methacrylate and poly(n-butyl methacrylate-co-lauryl methacrylate). The exemplary formulas of some of these copolymers are shown below as formulas (IV), (V), and (VI), respectively. Those having ordinary skill in the art understand that the formulas (IV), (V), and (VI) are not the only formulas that illustrate the structure of the copolymers, and that the structures can take other forms.



[0061] For a copolymer or a terpolymer, T_g (on the Kelvin scale) is generally the mass-fraction-weighted average of the polymer constituents, according to the Fox equation. Consequently, a copolymer or terpolymer of formulas (III-A to III-D) can be designed with a predetermined T_g value. For example, pure poly(lauryl methacrylate) has a T_g of about 208 K (-65°C .), and poly(n-butyl methacrylate) has a T_g of about 293 K (20°C .). Accordingly, poly(n-butyl methacrylate-co-lauryl methacrylate) (VI) [P(BMA-LMA)] having

from about 2 mass % to about 25 mass % of lauryl methacrylate units, and the balance derived from n-butyl methacrylate can have a T_g from about 17°C . to about -5°C ., as shown in Table 1.

TABLE I

Glass Transition Temperature of Poly(n-butyl methacrylate-co-lauryl methacrylate)		
No.	Mass Content of Lauryl Methacrylate in the Copolymer, %	T_g of the Copolymer, $^\circ \text{C}$.
1	2	17
2	5	14
3	10	8
4	25	-7

Physical Blends of Base Polymer with Other Acrylic Polymer(s)

[0062] In some embodiments, physical blends of base polymer with at least one other acrylic polymer where the T_g of the blend is lower than the T_g of pure base polymer can be used to make any or all layers of the stent coating. The T_g of a blend can be below about 20°C ., for example, from about -30°C . to about 20°C ., more narrowly, between about -15°C . to about 18°C ., for example, about 15°C .

[0063] Examples of acrylic polymers other than base polymer that can be combined with base polymer to form a blend include poly(n-hexyl methacrylate) (PHMA), poly(2-ethylhexyl methacrylate) (PEHMA), poly(n-octyl methacrylate), poly(2-ethoxyethyl methacrylate), poly(2-methoxyethyl methacrylate), poly(pentyl methacrylate), poly(iso-decyl methacrylate), poly(3,5,5-trimethylhexyl methacrylate), poly(n-decyl methacrylate), poly(n-dodecyl methacrylate), poly(1-hexadecyl methacrylate), poly(undecyl methacrylate), and poly(lauryl methacrylate) (PLMA).

[0064] As with copolymers, the T_g of a blend of individual polymer (on the Kelvin scale) is generally the mass-fraction-weighted average of the polymers comprising the blend as long as the blend is non-crystalline the blend polymers are miscible. Accordingly, a physical blend of base polymer with at least one other acrylic polymer can have a predetermined value of T_g , in these examples 15°C . Examples of blends containing about 92 mass % of base polymer and 8 mass % of poly(decyl methacrylate), and blends containing about 69 mass % of base polymer and 21 mass % of poly(2-ethyl hexyl methacrylate) are useful. Polymer blends can include blends of base-polymer-unit copolymers with at least one acrylic polymer other than a base polymer or a base-polymer-unit copolymer, for example poly(n-hexyl methacrylate) (PHMA), poly(2-ethylhexyl methacrylate) (PEHMA), poly(n-octyl methacrylate), poly(2-ethoxyethyl methacrylate), poly(2-methoxyethyl methacrylate), poly(pentyl methacrylate), poly(iso-decyl methacrylate), poly(3,5,5-trimethylhexyl methacrylate), poly(n-decyl methacrylate), poly(n-dodecyl methacrylate), poly(1-hexadecyl methacrylate), poly(undecyl methacrylate), and poly(lauryl methacrylate) (PLMA).

Compositions Including a Non-Acrylic Component

[0065] According to other embodiments of the present invention, some non-acrylic monomers or polymers can be

also used for making the stent coating. Some embodiments select non-acrylic monomers that polymerize by free radical or atom transfer process. Non-acrylic monomers are those that are substantially free of acrylic group (I) and of methacrylic group (II) shown above. Non-acrylic polymers are those that are derived from non-acrylic monomers. The term non-acrylic polymers includes non-acrylic homopolymers, copolymers, terpolymers, oligomers, and prepolymers.

[0066] In some embodiments, a copolymer of base-polymer-unit with a non-acrylic monomer(s) can be used in which the copolymer has a T_g below about 20° C., for example, from about -30° C. to about 18° C., alternatively, from about -15° C. to about 18° C., for example, about 15° C. Examples of non-acrylic monomers that can be copolymerized with a base-polymer-unit to form such a copolymer include those shown in Table II. The copolymers of a base-polymer-unit with a non-acrylic monomer(s) that can be used can be of any kind, e.g., random, alternating, or block-copolymers. The copolymers of a base-polymer-unit with a non-acrylic monomer(s) can be designed by those having ordinary skill in the art so that the copolymers have a predetermined value of T_g , as described above for the a base-polymer-unit copolymers having the formula (III-A) to formula (III-D).

[0067] In some embodiments, physical blends of base polymer with at least one non-acrylic polymer can be used for any or all layers of the stent coating, where the T_g of the blend is lower than that the T_g of pure base polymer.

[0068] The T_g of a blend can be below about 20° C., for example, from about -30° to about 20° C., more narrowly, from about -15° C. to about 18° C., for example, about 15° C.

TABLE II

Examples of non-acrylic polymers		
No.	Polymer	T_g , K
1	Poly(4-methoxycarbonyl-3-methyl-1-butenylene)	326
2	Poly(2-cyclohexylethylethylene)	313
3	Poly(hexadecylethylene)	328
4	Poly(iso-butylethylene)	302
5	Poly(iso-propylethylene), atactic	323
6	Poly(3,3-dimethylbutylethylene)	326
7	Poly(1,1,2-trimethylethylene)	310
8	Poly(4,4 dimethylpentylethylene)	313
9	Poly(propyl-2-propylene)	300
10	Poly(2,2,2-trifluoroethoxytrifluoroethylene)	308
11	Poly(4-methoxybenzoylethylene)	319
12	Poly(3,4-dimethoxybenzoylethylene)	315
13	Poly(vinyl fluoride)	314
14	Poly(vinyl acetate)	305
15	Poly(ethylene-co-vinyl alcohol)(EVAL)	328
16	Poly(cyclopentanoyloxyethylene)	309
17	Poly(formyloxyethylene), 60% syndiotactic	310
18	Poly(formyloxyethylene), 50% syndiotactic	306
19	Poly(4-(sec-butoxymethyl) styrene)	313
20	Poly(4-butoxystyrene)	320
21	Poly(3-ethylstyrene)	303
22	Poly(n-octyl acrylamide)	220
23	Poly(4-butylstyrene)	279
24	Poly(4-octylstyrene)	228
25	Poly(butoxyethylene)	218
26	Poly(butylene adipate)	223
27	Poly(oxybutylene)	185
28	Poly(vinylidene fluoride)	244

[0069] As in a of copolymers of a base-polymer-unit with non-acrylic monomers, for a blend of base polymer with individual non-acrylic polymers, the T_g of the blend (on the Kelvin scale) is generally the mass-fraction-weighted average of the polymers comprising the blend as given by the Fox equation. Accordingly, a physical blend of base polymer with at least one other non-acrylic polymer can have a predetermined value of T_g , for example 15° C. Examples of blends that can be used include a blend containing about 29 mass % of base polymer and 71 mass % of poly(4-butylstyrene) and a blend containing about 82 mass % of base polymer and 18 mass % of poly(vinylidene fluoride).

[0070] At least one of the drug-polymer layer or the topcoat layer can include a base-polymer-unit- or PBMA-based polymer or blend having T_g that falls within the previously described ranges. However, other polymers can also be used for the primer, drug-polymer, or top-coat layers so long as the polymer or a polymer blend forming either the drug-polymer layer or the topcoat layer have the T_g within the specified ranges.

[0071] Representative examples of alternative polymers that can be used for making the primer, drug-polymer, or topcoat layers are shown below.

polyvinyl ethers	polyvinyl methyl ether
polyvinylidene halides	polyvinylidene fluoride
	polyvinylidene chloride
polyvinyl aromatics	polystyrene
polyamides	Nylon 66
	polycaprolactam
biomolecules	fibrin
	fibrinogen
	cellulose
	starch
	collagen
	hyaluronic acid
poly(hydroxybutyrate-co-valerate)	
polydioxanone	
polyorthoester	
polyanhydride	
poly(glycolic acid)	
poly(D,L-lactic acid)	
poly(glycolic acid-co-trimethylene carbonate)	
polyphosphoester	
polyphosphoester urethane	
poly(amino acids)	
polycyanoacrylates	
poly(trimethylene carbonate)	
poly(iminocarbonate)	
co-poly(ether-esters)	
polyalkylene oxalates	
polyphosphazenes	
polyurethanes	
silicones	
polyesters	
polyolefins	
polyisobutylene	
ethylene-alphaolefin copolymers	
polyvinyl chloride	
poly(vinylidene fluoride-co-hexafluoropropene)	
polyacrylonitrile	
polyvinyl ketones	
polyvinyl esters	
acrylonitrile-styrene copolymers	
ABS resins	
ethylene-vinyl acetate copolymers	
alkyd resins	
polycarbonates	
polyoxymethylenes	
polyimides	

-continued

polyethers
 epoxy resins
 polyurethanes
 rayon
 rayon-triacetate
 cellulose
 cellulose acetate
 cellulose butyrate
 cellulose acetate butyrate
 cellophane
 cellulose nitrate
 cellulose propionate
 cellulose ethers
 carboxymethyl cellulose

[0072] The coating of the present invention has been described in conjunction with a stent. However, the coating can also be used with a variety of other medical devices. Examples of implantable medical device that can be used in conjunction with the embodiments of this invention include stent-grafts, grafts (e.g., aortic grafts), artificial heart valves, cerebrospinal fluid shunts, pacemaker electrodes, axius coronary shunts and endocardial leads (e.g., FINELINE and ENDOTAK, Guidant Corporation). The underlying structure of the device can be of virtually any design. The device can be made of a metallic material or an alloy such as, but not limited to, cobalt-chromium alloys (e.g., ELGILOY), stainless steel (316L), "MP35N," "MP20N," ELASTINITE (Nitinol), tantalum, tantalum-based alloys, nickel-titanium alloy, platinum, platinum-based alloys such as, e.g., platinum-iridium alloy, iridium, gold, magnesium, titanium, titanium-based alloys, zirconium-based alloys, or combinations thereof. Devices made from bioabsorbable or biostable polymers can also be used with the embodiments of the present invention.

[0073] "MP35N" and "MP20N" are trade names for alloys of cobalt, nickel, chromium and molybdenum available from Standard Press Steel Co. of Jenkintown, Pa. "MP35N" consists of 35% cobalt, 35% nickel, 20% chromium, and 10% molybdenum. "MP20N" consists of 50% cobalt, 20% nickel, 20% chromium, and 10% molybdenum.

[0074] The active agent, therapeutic substance or drug, the terms, which are used interchangeably, can include any substance capable of exerting a therapeutic or prophylactic effect for a patient. The drug may include small molecule drugs, peptides, proteins, oligonucleotides, and the like. The drug could be designed, for example, to inhibit the activity of vascular smooth muscle cells. It can be directed at inhibiting abnormal or inappropriate migration or proliferation of smooth muscle cells to inhibit restenosis.

[0075] Examples of drugs include antiproliferative substances such as actinomycin D, or derivatives and analogs thereof (manufactured by Sigma-Aldrich of Milwaukee, Wis., or COSMEGEN available from Merck). Synonyms of actinomycin D include dactinomycin, actinomycin IV, actinomycin I₁, actinomycin X₁, and actinomycin C₁. The active agent can also fall under the genus of antineoplastic, anti-inflammatory, antiplatelet, anticoagulant, antifibrin, antithrombin, antimitotic, antibiotic, antiallergic and antioxidant substances. Examples of such antineoplastics or antimitotics include paclitaxel (e.g. TAXOL® by Bristol-Myers Squibb Co., Stamford, Conn.), docetaxel (e.g. Taxotere®, from

Aventis S. A., Frankfurt, Germany) methotrexate, azathioprine, vincristine, vinblastine, fluorouracil, doxorubicin hydrochloride (e.g. Adriamycin® from Pharmacia & Upjohn, Peapack N.J.), and mitomycin (e.g. Mutamycin® from Bristol-Myers Squibb Co., Stamford, Conn.). Examples of such antiplatelets, anticoagulants, antifibrin, and antithrombins include sodium heparin, low molecular weight heparins, heparinoids, hirudin, argatroban, forskolin, vapirost, prostacyclin and prostacyclin analogues, dextran, D-phe-pro-arg-chloromethylketone (synthetic antithrombin), dipyridamole, glycoprotein IIb/IIIa platelet membrane receptor antagonist antibody, recombinant hirudin, and thrombin inhibitors such as Angiomax™ (Biogen, Inc., Cambridge, Mass.). Examples of such cytostatic or antiproliferative agents include angiopeptin, angiotensin converting enzyme inhibitors such as captopril (e.g. Capoten® and Capozide® from Bristol-Myers Squibb Co., Stamford, Conn.), cilazapril or lisinopril (e.g. Prinivil® and Prinzide® from Merck & Co., Inc., Whitehouse Station, N.J.); calcium channel blockers (such as nifedipine), colchicine, fibroblast growth factor (FGF) antagonists, fish oil (omega 3-fatty acid), histamine antagonists, lovastatin (an inhibitor of HMG-CoA reductase, a cholesterol lowering drug, brand name Mevacor® from Merck & Co., Inc., Whitehouse Station, N.J.), monoclonal antibodies (such as those specific for Platelet-Derived Growth Factor (PDGF) receptors), nitroprusside, phosphodiesterase inhibitors, prostaglandin inhibitors, suramin, serotonin blockers, steroids, thioprotease inhibitors, triazolopyrimidine (a PDGF antagonist), and nitric oxide. An example of an antiallergic agent is permirolast potassium. Other therapeutic substances or agents which may be appropriate include alpha-interferon, genetically engineered epithelial cells, tacrolimus, dexamethasone, and rapamycin and structural derivatives or functional analogs thereof, such as 40-O-(2-hydroxy)ethyl-rapamycin (known by the trade name of EVEROLIMUS available from Novartis), 40-O-(3-hydroxy)propyl-rapamycin, 40-O-[2-(2-hydroxy)ethoxy]ethyl-rapamycin, and 40-O-tetrazole-rapamycin.

EXAMPLES

[0076] Some embodiments of the present invention are further illustrated by the following examples.

Prophetic Example 1

[0077] A polymer solution containing from about 0.1 mass % to about 15 mass %, for example, about 2.0 mass % of EVAL and the balance, a solvent mixture of DMAC and ethanol, the solvent mixture containing about 80 mass % of DMAC to about 20 mass % of ethanol can be prepared. The solution can be applied onto a stent to form a primer layer. To apply the primer layer, a spray apparatus, such as an EFD 780S spray nozzle with a VALVEMATE 7040 control system (EFD, Inc. of East Providence, R.I.) can be used. The EFD 780S spray nozzle is an air-assisted external mixing atomizer. The composition is atomized by air and applied to the stent surfaces. During the process of applying the composition, the stent can optionally be rotated about its longitudinal axis, at a speed of about 50 to about 150 rpm. The stent can also be moved linearly along the same axis during the application.

[0078] The EVAL solution can be applied to a 13-mm TETRA stent (Guidant Corporation) in a series of 10-second

passes, to deposit, for example, 10 μg of coating per spray pass. Instead of the 13-mm TETRA stent, another suitable stent can be used, for example, a 12-mm VISION stent (also Guidant Corporation). Between the spray passes, the stent can be dried for about 10 seconds using flowing air with a temperature of about 60° C. Five spray passes can be applied, followed by baking the primer layer at about 110° C. for about 1-hour. As a result, a primer layer can be formed having a solids content of about 50 μg . "Solids" means the amount of the dry residue deposited on the stent after all volatile organic compounds (e.g., the solvent) have been removed.

[0079] A drug-containing formulation can be prepared comprising:

[0080] (a) from about 0.1 mass % to about 15 mass %, for example, about 2.0 mass % of EVAL;

[0081] (b) from about 0.1 mass % to about 2 mass %, for example, about 1.0 mass % of an active agent, for example, EVEROLIMUS; and

[0082] (c) the balance, a solvent mixture of DMAC and pentane, the solvent mixture containing about 80 mass % of DMAC and about 20 mass % of pentane.

[0083] In a manner identical to the application of the primer layer, five spray passes can be performed, followed by baking the drug-polymer layer at about 50° C. for about 2 hours, to form the drug-polymer layer having a solids content from about 30 μg and 750 μg , for example, about 90 μg , and a drug content of from about 10 μg to about 250 μg , for example, 30 μg .

[0084] Finally, a topcoat composition can be prepared, comprising:

[0085] (a) from about 1 mass % to about 10 mass %, for example, about 2 mass % of poly(n-butyl methacrylate) (PBMA) having weight average molecular weight of about 500,000; and

[0086] (b) the balance, a solvent mixture of acetone and cyclohexanone, the solvent mixture containing about 70 mass % of acetone and about 30 mass % of cyclohexanone.

[0087] In a manner identical to the application of the primer layer and the drug-polymer layer, a number of spray passes are performed followed by final baking at about 50° C. for about 1 hour. As a result, the topcoat membrane can be formed with a solids content of from about 40 μg to about 150 μg , for example, about 60 μg .

Prophetic Example 2

[0088] A stent can be coated as described in Prophetic Example 1, where PBMA in the topcoat can have a polydispersity index of about 4. The weight average molecular weight of PBMA can be from about 150,000 Daltons to about 400,000 Daltons.

Prophetic Example 3

[0089] A stent can be coated as described in Prophetic Example 1, except that in the topcoat layer PBMA can be replaced by the same amount of poly(n-butyl methacrylate-co-lauryl methacrylate) [P(BMA-LMA)] having from about 2 mass % to about 25 mass %, for example, about 10 mass

% of units derived from lauryl methacrylate, and the balance of units derived from n-butyl methacrylate. The solvent that can be used for dissolving Poly(BMA-LMA) prior to forming the topcoat layer can be a solvent mixture of acetone and cyclohexanone, the solvent mixture containing about 70 mass % of acetone and about 30 mass % of cyclohexanone.

Prophetic Example 4

[0090] A stent can be coated with a primer layer and a drug-polymer layer as described in Prophetic Example 1. A topcoat composition can be prepared, comprising:

[0091] (a) from about 1 mass % to about 10 mass %, for example, about 1.8 mass % PBMA;

[0092] (b) from about 0.1 mass % to about 10 mass %, for example, about 0.2 mass % poly(lauryl methacrylate) (PLMA); and

[0093] (c) the balance, a solvent mixture of acetone and xylene, the solvent mixture containing about 50 mass % of acetone and about 50 mass % of xylene.

[0094] In a manner like the application of the primer layer and the drug-polymer layer, a number of spray passes are performed followed by final baking at about 60° C. for about 1 hour. As a result, the topcoat membrane can be formed, the membrane having a solids content of from about 40 μg to about 120 μg , for example, about 75 μg .

Prophetic Example 5

[0095] A polymer solution containing from about 0.1 mass % to about 15 mass %, for example, about 2.0 mass % of PBMA and, the balance, a solvent mixture of acetone and cyclohexanone containing about 70 mass % of acetone to about 30 mass % of cyclohexanone can be prepared. The solution can be applied onto a stent to form a primer layer. To apply the primer layer, a spray apparatus, such as an EFD 780S spray nozzle with a VALVEMATE 7040 control system (EFD, Inc. of East Providence, R.I.) can be used. The EFD 780S spray nozzle is an air-assisted external mixing atomizer. The composition is atomized by air and applied to the stent surfaces. While applying the composition, the stent can optionally be rotated about its longitudinal axis, at a speed of about 50 to about 150 rpm. The stent can also be linearly moved along the same axis during the application.

[0096] The PBMA solution can be applied to a 12-mm small VISION stent (Guidant Corporation) in a series of 10-second passes, to deposit, for example, 10 μg of coating per spray pass. Between the spray passes, the stent can be dried for about 10 seconds using flowing air with a temperature of about 60° C. Five spray passes can be applied, followed by baking the primer layer at about 80° C. for about 1 hour. As a result, a primer layer can be formed having a solids content of about 50 μg . "Solids" means the amount of the dry residue deposited on the stent after all volatile organic compounds (e.g., the solvent) have been removed.

[0097] A drug-containing formulation can be prepared comprising:

[0098] (a) from about 0.1 mass % to about 15 mass %, for example, about 2.0 mass % of poly(n-butyl methacrylate-co-4-butylstyrene) wherein 66% of the mass is

derived from BMA units and 34% of the mass is derived from 4-butylstyrene units;

[0099] (b) from about 0.1 mass % to about 2 mass %, for example, about 0.8 mass % of an active agent, for example, SIROLIMUS; and

[0100] (c) the balance, a solvent mixture of acetone and 4-methyl-2-pentanone, the solvent mixture containing about 50 mass % of acetone and about 50 mass % of 4-methyl-2-pentanone.

[0101] In a manner identical to the application of the primer layer, nineteen spray passes can be performed, followed by baking the drug-polymer layer at about 50° C. for about 2 hours, to form the drug-polymer reservoir layer having a solids content from about 30 μg and 750 μg , for example, about 190 μg , and a drug content of from about 10 μg to about 250 μg , for example, 50 μg .

Prophetic Example 6

[0102] A stent can be coated with a primer layer as described in Prophetic Example 5. A drug reservoir composition can be prepared comprising:

[0103] (a) from about 1 mass % to about 10 mass %, for example, about 1.8 mass % PBMA;

[0104] (b) from about 0.1 mass % to about 10 mass %, for example, about 0.2 mass % poly(butylene adipate); and

[0105] (c) from about 0.1 mass % to about 2 mass %, for example, about 0.5 mass % of an active agent, for example, PACLITAXEL

[0106] (c) the balance, a solvent mixture of acetone and xylene, the solvent mixture containing about 50 mass % of acetone and about 50 mass % of xylene.

[0107] In a manner identical to the application of the primer layer, a number of spray passes are performed followed by final baking at about 60° C. for about 1 hour. As a result, a drug reservoir layer can be formed having a solids content of about 40 μg to about 200 μg , for example, about 125 μg .

[0108] While particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that changes and modifications can be made without departing from the embodiments of this invention in its broader aspects and, therefore, the appended claims are to encompass within their scope all such changes and modifications as fall within the true spirit and scope of the embodiments of this invention. Additionally, various embodiments have been described above. For convenience's sake, combinations of aspects composing invention embodiments have been listed in such a way that one of ordinary skill in the art may read them exclusive of each other when they are not necessarily intended to be exclusive. But a recitation of an aspect for one embodiment is meant to disclose its use in all embodiments in which that aspect can be incorporated without undue experimentation. In like manner, a recitation of an aspect as composing part of an embodiment is a tacit recognition that a supplementary embodiment exists in that specifically excludes that aspect. All patents, test procedures, and other documents cited in this specification are fully incorporated by reference to the

extent that this material is consistent with this specification and for all jurisdictions in which such incorporation is permitted.

[0109] Moreover, some embodiments recite ranges. When this is done, it is meant to disclose the ranges as a range, and to disclose each and every point within the range, including end points. For those embodiments that disclose a specific value or condition for an aspect, supplementary embodiments exist that are otherwise identical, but that specifically exclude the value or the conditions for the aspect.

What is claimed is:

1. A medical article comprising an implantable medical device having a base-polymer-unit-derived polymer with a degree of an elongation at failure from about 20% to about 500%.

2. The medical article of claim 1 wherein the implantable medical device is a stent.

3. The medical article of claim 1 wherein the polymer is a base polymer having a weight average molecular weight of about 200,000 Daltons to about 1,000,000 Daltons.

4. The medical article of claim 3 wherein the polymer comprises a base polymer having a polydispersity index of about 3 to about 6.

5. The medical article of claim 1 wherein the polymer comprises a base polymer having a polydispersity index of about 3 to about 6.

6. The medical article of claim 1 wherein the polymer includes a first acrylic monomer.


7. The medical article of claim 6 wherein the polymer is a copolymer of the base polymer and the first acrylic monomer.

8. The medical article of claim 7 wherein the first acrylic monomer is at least one of n-hexyl methacrylate, 2-ethyl-hexyl methacrylate, lauryl methacrylate (dodecyl methacrylate), n-octyl methacrylate, n-heptyl methacrylate, n-nonyl methacrylate, 2-ethoxyethyl methacrylate, 2-methoxyethyl methacrylate, pentyl methacrylate, iso-decyl methacrylate, n-decyl methacrylate, n-dodecyl methacrylate), 1-hexadecyl methacrylate, undecyl methacrylate, or 3,5,5-trimethylhexyl methacrylate.




9. The medical article of claim 6 wherein the polymer has a glass transition temperature below about 20° C.

10. The medical article of claim 9 wherein the glass transition temperature is about -30° C. to about 20° C.

11. The medical article of claim 1 wherein the polymer has the formulas



-continued



wherein X and X₁ are each, independently, a hydrogen atom or an alkyl group, R and R₁ are each, independently, a C₁ to C₁₂ straight chained or branched aliphatic radical, and m, n, and p are each integers in which m>0, n>0, and p≥0.

12. The medical article of claim 10 having a glass transition temperature below about 20° C.

13. The medical article of claim 11 having a glass transition temperature of -30° C. to about 20° C.

14. The medical article of claim 1 wherein the polymer comprises poly(n-butyl methacrylate) and a second polymeric material wherein the polymer has a substantially single glass transition temperature that is below about 20° C.

15. The medical article of claim 14 wherein the glass transition temperature of about -30° C. to about 20° C.

16. The medical article of claim 14 wherein the second polymeric material is at least one of poly(n-hexyl methacrylate), poly(n-heptyl methacrylate), poly(2-ethylhexyl methacrylate), poly(n-octyl methacrylate), poly(n-nonyl methacrylate), poly(2-ethoxyethyl methacrylate), poly(2-methoxyethyl methacrylate), poly(pentyl methacrylate), poly(isodecyl methacrylate), poly(n-decyl methacrylate), poly(1-hexadecyl methacrylate), poly(undecyl methacrylate), poly(3,5,5-trimethylhexyl methacrylate), or poly(lauryl methacrylate).

17. The medical article of claim 14 wherein the second polymeric material is a non-acrylic polymer with a T_g below that of the base polymer.

18. The medical article of claim 1 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, anti-

biotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

19. The medical article of claim 6 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

20. The medical article of claim 9 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

21. The medical article of claim 13 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

22. The medical article of claim 15 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

23. The medical article of claim 15 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetabolites, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

24. A method comprising depositing a coating on an implantable medical device wherein the coating has an elongation at failure of about 20% to about 500%.

25. The method of claim 24 wherein the implantable medical device is a stent.

26. The method of claim 24 wherein the polymer comprises a base polymer having a weight average molecular weight of about 200,000 Daltons to about 1,000,000-Daltons.

27. The method of claim 26 wherein the base polymer has a polydispersity index of about 3 to about 6.

28. The method of claim 24 wherein the base polymer has a polydispersity index of about 3 to about 6.

29. The method of claim 24 wherein the polymer includes a first acrylic monomer.

30. The method of claim 29 wherein the polymer is a copolymer of a base polymer and the first acrylic monomer.


31. The method of claim 29 wherein the first acrylic monomer is at least one of n-hexyl methacrylate, 2-ethylhexyl methacrylate, lauryl methacrylate (dodecyl methacry-

late), n-octyl methacrylate, n-heptyl methacrylate, n-nonyl methacrylate, 2-ethoxyethyl methacrylate, 2-methoxyethyl methacrylate, pentyl methacrylate, iso-decyl methacrylate, n-decyl methacrylate, n-dodecyl methacrylate, 1-hexadecyl methacrylate, undecyl methacrylate, or 3,5,5-trimethylhexyl methacrylate.

32. The method of claim 29 wherein the polymer has a glass transition temperature below about 20° C.

33. The method of claim 32 wherein the glass transition temperature of about -30° C. to about 20° C.

34. The method of claim 24 wherein the polymer has at least one of the formulas:



wherein X and X₁ are each, independently, a hydrogen atom or an alkyl group, R and R₁ are each, independently, a C₁ to C₁₂ straight chained or branched aliphatic radical, and m, n, and p are each integers in which m>0, n>0, and p≥0.

35. The method of claim 34 wherein the polymer has a glass transition temperature below about 20° C.

36. The method of claim 35 wherein the glass transition temperature of -30° C. to about 20° C.

37. The method of claim 24 wherein the polymer comprises a base polymer and a second polymer wherein the polymer substantially has a single glass transition temperature that is below about 20° C.

38. The method of claim 37 wherein the glass transition temperature of -30° C. to about 20° C.

39. The method of claim 37 wherein the second polymer is at least one of poly(n-hexyl methacrylate), poly(n-heptyl methacrylate), poly(2-ethylhexyl methacrylate), poly(n-octyl methacrylate), poly(n-nonyl methacrylate), poly(2-ethoxyethyl methacrylate), poly(2-methoxyethyl methacrylate), poly(pentyl methacrylate), poly(iso-decyl methacrylate), poly(n-decyl methacrylate), poly(1-hexadecyl methacrylate), poly(undecyl methacrylate), poly(3,5,5-trimethylhexyl methacrylate), or poly(lauryl methacrylate).

40. The method of claim 37 wherein the second polymer is a non-acrylic polymer with a Tg below that of the base polymer.

41. The method of claim 24 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

42. The method of claim 29 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

43. The method of claim 33 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

44. The method of claim 36 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

45. The method of claim 37 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

46. The method of claim 39 wherein the medical device additionally comprises one or any combination of vascular-smooth-muscle-cell-activity inhibitors, antiproliferatives, antineoplastics, antimetotics, anti-inflammatories, antiplatelets, anticoagulants, antifibrins, antithrombins, antibiotics, antiallergics, antioxidants, and any prodrugs, metabolites, analogs, homologues, congeners, derivatives, or salts of these.

47. The medical device of claim 1 wherein the base polymer is at least one of or any combination of poly(n-butyl methacrylate), poly(ethyl methacrylate), poly(isopropyl methacrylate), or poly(n-propyl methacrylate).

